

Chemically Treated PET Layer <

PET Core Layer

Peelable PET Layer 4

SUPCOAT BT 7011 HWX

Description

SUPCOAT BT 7011 HWX is a transparent biaxially oriented polyester (BOPET) film with peelable seal property. Other side is treated.

It has high resistant to water. Specially designed for water caps.

Properties

- Peelable seal to APET
- Superior mechanical strength
- Excellent stiffness
- Excellent machinability and flatness
- · Good dimensional stability
- Excellent chemical resistance
- Easy open peelable seals

Applications

It is specially designed for use in lidding applications where peelable seal property is needed to APET.

Treated side may be used as printing and lamination surface, but should be approved with present ink and glue systems used including aging tests.

Please contact customer service representetive for the application compliance.



Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921



Technical Features

PROPERTIES	TEST METHOD	UNITS		BT 7011 HWX	
THICKNESS	ASTM	micron		18	33
	F2251	Gauge		72	132
YIELD	ASTM	m²/kg		41,7	22,
	D4321	in²/Lbs		29.300	15628
UNIT WEIGHT	ASTM D4321	g/m²		24	45
GLOSS (45 °)	ASTM D2457	%		70	70
OXYGEN TRANSMISSION RATE (23°C-0%RH)	ASTM D3985	cc/m²/24hrs		≤ 100	≤ 100
		cc/100in ² /24hrs		≤ 6,5	≤ 6,5
WATER VAPOUR TRANSMISSION RATE (38°C-90%RH)	ASTM F1249	g/m²/24hrs		≤ 30	≤ 30
		g/100in²/24hrs		≤2	≤2
TENSILE	ASTM D882	MD	N/mm²	240	240
			lb/in²	34.800	34800
STRENGTH AT BREAK		TD	N/mm ²	260	260
			lb/in²	37.700	37700
ELONGATION	ASTM D882	MD	%	140	140
AT BREAK		TD		110	110
THERMAL	ASTM D1204	MD	0/	2,0	2,0
SHRINKAGE (150 °C, 30 min, air)		TD	%	0,5	0,5
COEFFICIENT	ASTM D1894	Coated Side/Metal		0,50	0,50
OF FRICTION		Other Side/Metal		0,40	0,40
SURFACE TENSION	ASTM D2578	Dura (am	Chemical Side	48	48
		Dyne/cm Other Side		-	-
HEATSEAL RANGE	ASTM F88	°C		90-240	90-240
		°F		194-464	194-464
HEATSEAL STRENGTH to APET (150 °C, 4 MPa, 1 s)	Internal	N/15mm		3,5	3,5

Product Identification (Decision 97/129/EC): PET1

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability..

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm				



Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921

REV: 06 Date: 20.08.2022