

Printable Topcoated Layer

PET Core Layer 4

Peelable PET Layer

# SUPCOAT BT 7011 PPM

## Description

SUPCOAT BT 7011 PPM is a transparent biaxially oriented polyester (BOPET) film with peelable seal property on one side. Other side is topcoated for excellent printable and adhesion property with broad range of ink systems including UV print technology. Top coating formulation is designed to resist humidity.

Any possible caution for blocking tendency during printing and/or other process should be taken since the film is both sides coated.

## **Properties**

- Peelable seal to PP
- Superior mechanical strength
- Excellent stiffness
- Excellent machinability and flatness
- Good dimensional stability
- Excellent chemical resistance
- · Easy open peelable seals
- Suitable for punching or side cutting.
- The film shelf life is 6 months

#### Applications

It is specially designed for use in lidding applications where peelable seal property is needed to wide range of substrates like PP.

Please contact customer service representetive for the application compliance.



Superfilm Europe S.A 37 Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921



### **Technical Features**

PROPERTIES	TEST METHOD	UNITS		BT 7011 PPM		
THICKNESS	ASTM F2251	micron		40	54	
		Gauge		160	216	
YIELD	ASTM D4321	m²/kg		18,4	13,5	
		in²/Lbs		12.900	9.500	
UNIT WEIGHT	ASTM D4321	g/m²		54,4	74	
HAZE	ASTM D1003	%		20		
GLOSS (45 °)	ASTM D2457	%		75		
OXYGEN	ASTM D3985	cc/m²/24hrs		≤ 100		
TRANSMISSION RATE (23°C-0%RH)		cc/100in <sup>2</sup> /24hrs		≤ 6,5		
WATER VAPOUR	ASTM F1249	g/m²/24hrs		≤ 30		
TRANSMISSION						
(38°C-90%RH)		g/100in²/24hrs		≤ 2		
	ASTM D882	MD	N/mm²	240		
TENSILE STRENGTH AT		TD	lb/in² N/mm²	34.800 260		
BREAK			lb/in <sup>2</sup>	37.700		
	ASTM D882	MD	10/111		140	
ELONGATION AT BREAK		TD	%	110		
THERMAL	ASTM D1204	MD		2,0		
SHRINKAGE (150 °C, 30 min, air)		TD	%	0,5		
COEFFICIENT	ASTM D1894	Topcoat Side/Metal		0,45		
OF FRICTION		Other Side/Metal		0,40		
SURFACE TENSION	ASTM D2578	Dyne/ cm	Topcoat Side	38		
			Peelable- Side			
	ASTM F88	°C		160-240		
HEATSEAL RANGE		°F		320-464		
HEATSEAL STRENGTH to PP (190 °C, 4 MPa, 1 s) Product Identification	Internal	N/15mm		5,0		

**Regulatory Status** 

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS						
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE			
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm			



Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A 37 Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921

REV: 02 Date: 20.03.2025