

Chemically Treated PET Layer

PET Core Layer

Pealable PET Layer 🔺

SUPCOAT BT 7011 PPC

Description

SUPCOAT BT 7011 PPC is a transparent biaxially oriented polyester (BOPET) film with peelable seal property. Other side is treated.

Please contact with our sales departmant for other available thicknesses.

Properties

- Peelable seal to PP,PS
- Superior mechanical strength
- Excellent stiffness
- Excellent machinability and flatness
- Good dimensional stability
- Excellent chemical resistance
- Easy open peelable seals
- Suitable for microwave & conventional oven
- •The film shelf life is 6 months

Applications

It is specially designed for use in lidding applications where peelable seal property is needed to substrates like PP.

Treated side may be used as printing surface, but should be approved with present ink and glue systems used including aging tests.

Please contact customer service representetive for the application compliance.



Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921



Technical Features

PROPERTIES	TEST METHOD	UI	NITS			BT 7011 PPC			
THICKNESS	ASTM F2251	m	icron	18	22	26	33	39	
		Gauge		72	88	104	132	156	
YIELD	ASTM D4321	m²/kg		41,6	33,8	28,4	22,2	18,7	
		in²/Lbs		29300	23.800	20.000	15600	13.200	
UNIT WEIGHT	ASTM D4321	g/m²		24	29,6	35,2	45	53,4	
HAZE	ASTM D1003	%		20					
GLOSS (45 °)	ASTM D2457		%		75				
OXYGEN TRANSMISSION	ASTM D3985	cc/m²/24hrs		≤ 100					
RATE (23°C-0%RH)		cc/100in ² /24hrs		≤ 6,5					
WATER VAPOUR		g/m²/24hrs		≤ 30					
TRANSMISSION RATE (38°C-90%RH)	ASTM F1249	g/100in²/24hrs		≤2					
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm²	240					
			lb/in²	34.800					
		TD	N/mm²	260					
			lb/in²			37.700			
ELONGATION AT BREAK	ASTM D882	MD	%	140 110					
	2002	TD		2,0					
THERMAL	ASTM D1204	MD TD	%	0,5					
(150 °C, 30 min, air)			Side/Metal	0,45					
COEFFICIENT OF FRICTION	ASTM D1894	Other Side/Metal		0,40					
	ASTM D2578	Chemical		38					
SURFACE TENSION		Dyne/cm	Side Other Side	-					
HEATSEAL	ASTM F88	°C		160-240					
RANGE		°F		320-464					
HEATSEAL STRENGTH to PP,PS (190 °C, 4 MPa, 1 s) Product Identification	Internal	N/15mm		5,0					

Product Identification (Decision 97/129/EC)

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm				



Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 REV: 09 Date: 20.03.2025

Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921