



## SUPLAIN

### 1311 MTE

#### Description

SUPLAIN 1311 MTE is both sides matt, biaxially oriented polypropylene film with better transparency property. One side treated. No heat seal property.

Both sides matt film for high value added products. It can be used as single ply surface print and/or lamination applications. Matt finish layer gives non-reflective surface. Special use as base film for baby diaper tapes.

#### Properties

- Matt appearance on both sides
- Better transparency
- Excellent ink and coating adhesion
- Low static property
- Resistance to chemicals, greases and oils
- Excellent machinability
- Excellent dimensional stability
- Good moisture barrier

## Technical Features

PROPERTIES	TEST METHOD	UNITS	1311 MTE	
THICKNESS	ASTM F2251	micron	35	40
		Gauge	140	160
YIELD	ASTM D4321	m <sup>2</sup> /kg	33,6	29,4
		in <sup>2</sup> /Lbs	23.600	20.700
UNIT WEIGHT	ASTM D4321	g/m <sup>2</sup>	29,8	34,0
HAZE	ASTM D1003	%	94	
GLOSS (45 °)	ASTM D2457	%	9	
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm <sup>2</sup>	140
			lb/in <sup>2</sup>	20.300
		TD	N/mm <sup>2</sup>	250
			lb/in <sup>2</sup>	36.300
ELONGATION AT BREAK	ASTM D882	MD	% 190	
		TD	% 70	
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	% 3	
		TD	% 1	
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,30	
		Film/Metal	0,20	
SURFACE TENSION	ASTM D2578	Dyne/cm	Treated Side	38
			Other Side	-

### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

**For related spec sheet with tolerance values, please contact our sales departments**