

Acrylic Coated Layer

Polypropylene Core Layer

Acrylic Coated Layer

SUPCOAT 7012 A2C

Description

SUPCOAT 7012 A2C is a transparent, both sides acrylic coated, biaxially oriented polypropylene (BOPP) film with improved aroma barrier.

Both sides are acrylic coated and receptive to inks and lamination glues makes it suitable for single web and laminations applications.

Properties

- Both sides acrylic coated
- Improved barrier to aroma
- · Low sealing threshold and broad seal range
- · Excellent hot tack and heat seal strength
- High clarity and gloss
- Excellent ink and lamination adhesion

Applications

Specially designed for overwrapping packaging applications. Acrylic coated side provides gas & aroma barrier and excellent support for printing.

It has low sealing threshold and broad sealing range with excellent hot tack property to be used at high speed packaging applications.



Factory & Head Office Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921



Technical Features

PROPERTIES	TEST METHOD			7012 A2C					
	ASTM F2251	micron		20	25	30	35	40	50
THICKNESS		Gauge		80	100	120	140	160	200
		m²/kg		54,4	43,6	36,4	31,2	27,3	21,9
YIELD	ASTM D4321	in²/Lbs		38.300	30,700	25.600	22.000	19.200	15.400
UNIT WEIGHT	ASTM D4321	g/m²		18,4	22,9	27,5	32,0	36,6	45,7
HAZE	ASTM D1003	%		1.7					
GLOSS (45 °)	ASTM D2457	%		90					
OXYGEN TRANSMISSION RATE (23°C-0%RH)	ASTM D3985	cc/m²/24hrs		≤ 1.000					
		cc/100in ² /24hrs		≤ 65					
WATER VAPOUR TRANSMISSION RATE (38°C-90%RH)	ASTM F1249	g/m²/24hrs		≤ 5					
		g/100in²/24hrs		≤ 0,45					
	ASTM D882	MD	N/mm²	170					
TENSILE STRENGTH AT			lb/in²	24.600					
BREAK		TD	N/mm ² Ib/in ²	300 43.400					
ELONGATION	ASTM D882	MD	%	170					
AT BREAK		TD		60					
THERMAL SHRINKAGE	ASTM D1204 ASTM D1894	MD	%	3					
(120 °C, 5 min, air)		TD		1					
COEFFICIENT OF FRICTION		Acrylic/Acrylic		0,30 0,20					
SURFACE	ASTM D2578	Acrylic Dyne/c Side		38					
TENSION		m	Acrylic Side	38					
HEATSEAL	ASTM F88	°C		90-145					
		°F		194-293					
HEATSEAL STRENGTH (120 °C, 1 MPa, 1 s) Product Identification	ASTM F88	N/15mm		2,5					

Product Identification (Decision 97/129/EC): PP5

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm				



Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921

REV: 04 Date: 17.12.2021