



# SUPCOAT 7011 L1C

## **Description**

SUPCOAT 7011 L1C is a transparent, one side acrylic coated, biaxially oriented polypropylene (BOPP) film with aroma barrier property. Non-treated layer has low temperature seal (LTS) down to 90°C (194°F).

# **Properties**

- · One side acrylic coated
- · Excellent wide sealing range with LTS on other side
- Improved barrier to aroma
- · High clarity and gloss
- · Excellent ink adhesion on acrylic side

# **Applications**

Acrylic coated side provides gas & aroma barrier and excellent support for printing. Low temperature sealable layer is suitable for high speed HFFS machines for making units and/or multiple packs.

Acrylic and LTS coatings are not seal compatible.





### **Technical Features**

PROPERTIES	TEST METHOD	U	NITS	7011 L1C				
THICKNESS	ASTM F2251	micron		20	25	30	40	
		Gauge		80	100	120	160	
YIELD	ASTM D4321	m²/kg		54,7	43,8	36,6	27,4	
		in²/Lbs		38.400	30.800	26.000	19.300	
UNIT WEIGHT	ASTM D4321	g/m²		18,3	22,8	27,3	36,5	
HAZE	ASTM D1003	%		2				
GLOSS (45°)	ASTM D2457	%		90				
OXYGEN TRANSMISSION	ASTM D3985	cc/m²/24hrs		≤1.000				
RATE (23°C-0%RH)		cc/100in²/24hrs		≤ 65				
WATER VAPOUR	ASTM F1249	g/m²/24hrs		≤ 5				
TRANSMISSION RATE (38°C-90%RH)		g/100in²/24hrs		≤ 0,32				
	ASTM D882	N/mm² MD		150				
TENSILE STRENGTH AT		IVID	lb/in²	21.700				
BREAK		TD	N/mm²	290				
			lb/in²	42.000				
ELONGATION AT BREAK	ASTM D882	MD	%	200				
		TD		70				
THERMAL SHRINKAGE	ASTM D1204	MD %		3 1				
(120 °C, 5 min, air)		Acrylic /Acrylic		0,30				
COEFFICIENT OF FRICTION	ASTM D1894	LTS/LTS		0,30				
SURFACE	ASTM D2578	Acrylic Dyne Side		38				
TENSION		/cm	LTS Side	-				
HEATSEAL RANGE	ASTM F88	°C	LTS/ LTS	80-145				
		°F	LIS	176-293				
HEATSEAL STRENGTH (90 °C, 1 MPa, 1 s)	ASTM F88	N/15 mm	LTS/ LTS	2,0				

Product Identification (Decision 97/129/EC): PP5

#### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm				



REV: 05 Date: 26.01.2023 Superfilm Europe S.A