



SUPWHITE

2212 MO

Description

SUPWHITE 2212 MO is a white pigmented, coextruded biaxially oriented polypropylene (BOPP) film. Both sides heat sealable and treated.

White colored heat sealable film for general packaging applications. Use on a wide range of packaging machines.

It can be used as single ply surface print and lamination substrate to itself and other films. It is also used for cold seal applications.

White color also saves white base color print.

Any possible caution for blocking tendency during printing process should be taken since the films are both sides treated.

Properties

- Higher whiteness and opacity
- Excellent heat seal strength and hot tack
- Outstanding opacity and gloss
- Good hot slip
- Excellent dimensional stability
- Excellent resistance to chemicals, greases and oil
- Excellent ink and coating adhesion
- Broad seal range

Technical Features

PROPERTIES	TEST METHOD	UNITS	2212 MO		
THICKNESS	ASTM F2251	micron	18	20	30
		Gauge	72	80	120
YIELD	ASTM D4321	m ² /kg	55,6	50,0	33,3
		in ² /Lbs	39.100	35.200	23.400
UNIT WEIGHT	ASTM D4321	g/m ²	18,0	20,0	30,0
GLOSS (45 °)	ASTM D2457	%	55		
LIGHT TRANSMISSION	ASTM D1746	%	30	28	25
OPACITY	DIN 53146	%	75	75	80
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	140	
			lb/in ²	20.300	
		TD	N/mm ²	230	
			lb/in ²	33.400	
ELONGATION AT BREAK	ASTM D882	MD	%	180	
		TD		60	
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	%	3	
		TD		1	
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,35		
		Film/Metal	0,20		
SURFACE TENSION	ASTM D2578	Dyne/cm	Treated Side	38	
			Other Side	38	
HEATSEAL RANGE	ASTM F88	°C	105 - 145		
		°F	221 - 293		
HEATSEAL STRENGTH (120 °C, 1 MPa, 1 s)	ASTM F88	N/15mm	2,0		

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments