

Printable Aluminium Layer Modified Layer White Opaque Cavitated Core Layer Modified Layer Polypropylene Layer (Treated for 1132 SGM)

SUPMET 1131 SGM / 1132 SGM

Description

SUPMET 1131 SGM and 1132 SGM are a white opaque, metallized, cavitated, biaxially oriented polypropylene (BOPP) film. Other side is treated for 1132 SGM. No heat seal property.

Specially designed for high speed roll-fed labelling applications as surface print single web substrate for beverages,

carbonated drinks, water and vegetable oil bottles.

Glossy metallic appearance for bright graphic designs.

Primering onto metal surface for adequate ink adhesion is highly recommended.

Properties

- Moderate density and yield
- · Improved stiffness for excellent machinability
- Brilliant metallic appearance
- Excellent dimensional stability and cuttability
- Resistance to curl
- The film shelf life is 6 months for 1131 SGM, 3 months for 1132 SGM



Factory & Head Office Başpınar (Organize) OSB Mahallesi O.S.B 2. Bölge Hacı Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A 37 Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921



Technical Features

PROPERTIES	TEST METHOD	UNITS		1131 SGM	1132 SGM	
THICKNESS	ASTM F2251	micron		38		
		Gauge		152		
YIELD	ASTM	m²/kg		36,5		
	D4321	in²/Lbs		25.700		
UNIT WEIGHT	ASTM D4321	g/m²		27,4		
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	80		
			lb/in²	11.600		
		TD	N/mm ²	170		
			lb/in ²	24.7	700	
ELONGATION	ASTM D882	MD	%	11	0	
AT BREAK		TD	/0	4()	
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	%	3		
		TD	70	1		
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film		0,35		
		Film/Metal		0,25		
SURFACE TENSION	ASTM D2578	Dyne/ cm	Metal Side	-		
			Other Side	-	38	
OPTICAL DENSITY	INTERNAL	-		2,5		

"Product Identification (Decision 97/129/EC): PP5"

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The film can also be supplied with ISCC+ certified raw materials with the category of bio-circular feedstock under the product group of SUPRENEW and category of circular feedstock under the product group of SUPCYCLE. SUPRENEW and SUPCYCLE products are certified with "Mass Balance" chain of custody system under ISCC+ and due to chemical processing of the feedstock, there is no compromise & change on any specific feature of the film given in this TDS regardless of the sustainable content in the film. Therefore all product properties of this film covers the same product code with SUPRENEW or SUPCYCLE brand. Three digits will be added to the end of the ISCC+ certified product code. SUPRENEW products will be differentiated with Rxx (R will communicate that the film is circular xx code will communicate the sustainable content % of the film) and SUPCYCLE products will be differentiated with Pxx (P will communicate that the film is circular xx code will communicate the sustainable content % of the film). Further details of the sustainable content of the film will be given in the Sustainability Declaration (SD) prepared for each ISCC+ certified order.

Metallization is a special process and aluminium coated surface is very sensitive to environmental conditions. Even though metal surface tension is above 40 dynes after production, it tends to decrease within time influencing by climatic conditions and storage periods. A guarantee of the duration of surface tension of metallized surface can not be given. We recommend to store metallized films in a dry place and at temperatures below 30°C. It is also advised to use metallized films as 'First in, First Out' principle. In-line treatment and/or primering onto metal surface for adequate ink or coating adhesion is strongly recommended. The metallized surface can normally be laminated with most of the substrates. Other properties of the metallized films are guaranteed for 6 months from the date of production.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm *	± % 5 for ≤ 390 mm OD ± % 10 for > 390 mm OD	- 0 & + 4 mm				

* 790 mm OD is available for BOPP films above 350 mm width

REV: 03 Date: 21.03.2025



Baspinar (Organize) OSB Mahallesi O.S.B 2. Bölge Haci Sani Konukoğlu Bulvarı No:1 P +90 342 211 60 00 (20 lines) F +90 342 337 28 70 Superfilm Europe S.A 37 Esplanade de la Moselle 90, Wasserbillig, Luxembourg P +352 261 19 922 F+352 261 19 921