



# SUPMET

## 1332 PX

### Description

SUPMET 1332 PX is a both sides matt biaxially oriented polypropylene (BOPP) film designed for label applications, preferably for In-Mould Labelling (IML). No heat seal property. Other side is treated.

It is specially designed for In-Mould Labelling (IML) for PP and PE based injection moulding as well as wrap-around, cut&stack labelling applications. It is suitable for gravure, flexo, UV & oxidative offset, letterpres and screen printing.

Any possible caution for blocking tendency during printing and/or other process should be taken since the film is both sides treated.

### Properties

- Matt appearance on both sides
- Metallic Gloss Effect
- Excellent web flatness and good dimensional stability
- Excellent die cutting properties
- Applicable for sheet-fed applications
- Required level of anti-static properties at all processes
- Excellent ink adhesion
- Resistance to chemicals, greases, oil, fruit acid and sugar
- The film shelf is 3 months

## Technical Features

PROPERTIES	TEST METHOD	UNITS	1332 PX	
THICKNESS	ASTM F2251	micron	52	62
		Gauge	208	248
YIELD	ASTM D4321	m <sup>2</sup> /kg	21,1	17,7
		in <sup>2</sup> /Lbs	14.900	12.500
UNIT WEIGHT	ASTM D4321	g/m <sup>2</sup>	47,2	56,4
GLOSS (45 °)	ASTM D2457	%	83	
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm <sup>2</sup>	135
			lb/in <sup>2</sup>	19.600
		TD	N/mm <sup>2</sup>	235
			lb/in <sup>2</sup>	34.100
ELONGATION AT BREAK	ASTM D882	MD	250	
		TD	70	
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	3	
		TD	1	
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,30	
		Film/Metal	0,20	
SURFACE TENSION	ASTM D2578	Dyne/cm	Metal Side	-
			Other Side	38
OPTICAL DENSITY	INTERNAL	-	1,0	

### “Product Identification (Decision 97/129/EC): PP5”

#### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The film can also be supplied with ISCC+ certified raw materials with the category of bio-circular feedstock under the product group of SUPRENEW and category of circular feedstock under the product group of SUPCYCLE. SUPRENEW and SUPCYCLE products are certified with “Mass Balance” chain of custody system under ISCC+ and due to chemical processing of the feedstock, there is no compromise & change on any specific feature of the film given in this TDS regardless of the sustainable content in the film. Therefore all product properties of this film covers the same product code with SUPRENEW or SUPCYCLE brand. Three digits will be added to the end of the ISCC+ certified product code. SUPRENEW products will be differentiated with Rxx (R will communicate that the film is circular xx code will communicate the sustainable content % of the film) and SUPCYCLE products will be differentiated with Pxx (P will communicate that the film is circular xx code will communicate the sustainable content % of the film). Further details of the sustainable content of the film will be given in the Sustainability Declaration (SD) prepared for each ISCC+ certified order.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

**For related spec sheet with tolerance values, please contact our sales departments**

STANDARD ROLL DIMENSIONS			
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm *	± % 5 for ≤ 390 mm OD ± % 10 for > 390 mm OD	- 0 & + 4 mm

\* 790 mm OD is available for BOPP films above 350 mm width